

DIC.PPS FZ-6600-B2

Polyphenylene Sulfide

DIC Corporation

Message:

Outline: FZ-6600-B2 is a glass fiber and mineral filled polyphenylene sulfide compound that is well balanced with excellent engineering properties and high flowability.

Color: Black and Natural (off white)

General Information			
UL YellowCard	E53829-243762		
Filler / Reinforcement	Glass\Mineral		
Features	High Flow		
UL File Number	E53829		
Appearance	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.89	g/cm ³	ASTM D792
Molding Shrinkage			ASTM D955
Flow	0.25	%	
Across Flow	1.0	%	
Water Absorption (23°C, 24 hr)	0.020	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785
M-Scale	100		
R-Scale	121		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	18000	MPa	ASTM D638
Tensile Strength	140	MPa	ASTM D638
Tensile Elongation (Break)	1.0	%	ASTM D638
Flexural Modulus	17000	MPa	ASTM D790
Flexural Strength	230	MPa	ASTM D790
Compressive Strength	170	MPa	ASTM D695
Poisson's Ratio	0.34		
Coefficient of Friction ¹			ASTM D1894
vs. Steel - Dynamic	0.35		
vs. Steel - Static	0.35		
Flexural Elongation at Break	1.7	%	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	80	J/m	ASTM D256

Unnotched Izod Impact	350	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	265	°C	ASTM D648
CLTE			ASTM D696
Flow : -30 to 90°C	1.8E-5	cm/cm/°C	
Transverse : -30 to 90°C	1.8E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Dielectric Strength (1.60 mm)	16	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	5.00		ASTM D150
Dissipation Factor (1 MHz)	6.0E-3		ASTM D150
Arc Resistance	180	sec	ASTM D495
Comparative Tracking Index	250	V	ASTM D3638
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.800 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Rear Temperature	300 to 340	°C	
Middle Temperature	300 to 340	°C	
Front Temperature	300 to 340	°C	
Mold Temperature	120 to 150	°C	
NOTE			
1.	P=150KPa, V=0.3m/s		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

