

Sindustris ABS LHF491G

Acrylonitrile Butadiene Styrene

Sincerity Australia Pty Ltd.

Message:

Sindustris ABS LHF491G is an Acrylonitrile Butadiene Styrene (ABS) material. It is available in Asia Pacific for injection molding.

Important attributes of Sindustris ABS LHF491G are:

Flame Rated

High Flow

Typical application of Sindustris ABS LHF491G: Electrical/Electronic Applications

General Information			
Features	High Flow		
Uses	Electrical/Electronic Applications		
UL File Number	E306922		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	53	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.40 to 0.70	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	106		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹ (3.20 mm)	2150	MPa	ASTM D638
Tensile Strength ² (Yield, 3.20 mm)	43.1	MPa	ASTM D638
Tensile Elongation ³ (Yield, 3.20 mm)	30	%	ASTM D638
Flexural Modulus ⁴ (3.20 mm)	2400	MPa	ASTM D790
Flexural Strength ⁵ (3.20 mm)	70.6	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-30°C, 3.20 mm	120	J/m	
-30°C, 6.40 mm	120	J/m	
23°C, 3.20 mm	260	J/m	
23°C, 6.40 mm	250	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	88.0	°C	
1.8 MPa, Unannealed, 6.40 mm	85.0	°C	
Vicat Softening Temperature	93.0	°C	ASTM D1525 ⁶
RTI Elec	60.0	°C	UL 746
RTI Imp	60.0	°C	UL 746
RTI Str	60.0	°C	UL 746

Electrical	Nominal Value	Unit	Test Method
Arc Resistance	6.00	sec	ASTM D495
Comparative Tracking Index (CTI) ⁷	PLC 1		IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 to 4.0	hr	
Suggested Max Moisture	0.010	%	
Rear Temperature	180 to 200	°C	
Middle Temperature	190 to 210	°C	
Front Temperature	200 to 220	°C	
Nozzle Temperature	200 to 230	°C	
Processing (Melt) Temp	210 to 240	°C	
Mold Temperature	40.0 to 70.0	°C	
Back Pressure	29.4 to 58.8	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	1.0 mm/min		
2.	50 mm/min		
3.	50 mm/min		
4.	15 mm/min		
5.	15 mm/min		
6.	Rate A (50°C/h), Loading 2 (50 N)		
7.	Solution A		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

