

Lion Idemitsu Composites PPS G140C1

Polyphenylene Sulfide

Lion Idemitsu Composites Co., Ltd.

Message:

Lion Idemitsu Composites PPS G140C1 is a Polyphenylene Sulfide (PPS) product filled with 40% glass fiber. It is available in Asia Pacific.

Characteristics include:

Flame Rated

High Strength

General Information			
Filler / Reinforcement	Glass Fiber,40% Filler by Weight		
Features	High Strength		
Appearance	Black		
Part Marking Code (ISO 11469)	>PPS-GF40<		
Physical	Nominal Value	Unit	Test Method
Density	1.60	g/cm ³	ISO 1183
Molding Shrinkage ¹			ISO 294-4
Across Flow	0.70	%	
Flow	0.40	%	
Water Absorption (23°C, 24 hr)	> 0.020	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	101		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	190	MPa	ISO 527-2
Tensile Strain (Break)	2.2	%	ISO 527-2
Flexural Modulus	12100	MPa	ISO 178
Flexural Stress	271	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength	11	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	264	°C	ISO 75-2/A
CLTE			ISO 11359-2
Flow	2.2E-5	cm/cm/°C	
Transverse	2.8E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms · cm	ASTM D257
Electric Strength (3.00 mm)	13	kV/mm	IEC 60243-1
Dielectric Constant	3.90		IEC 60250
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.800 mm)	V-0		UL 94

Additional Information	Nominal Value	Unit	Test Method
Flowability ² (1.00 mm)	8.80	cm	Internal Method
NOTE			
1.	Internal Method		
	Thickness 1mm, Cylinder temperature 320°C, Injection pressure 100MPa, Mold temperature 135°C		
2.			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

