Karina IVORY PVC COMPOUND 851D35/

1-B-IS-BZ

Polyvinyl Chloride

Karina Ind. e Com. de Plásticos Ltda

Message:

HEAVY METAL FREE PVC COMPOUND FOR EXTRUSION OF AUTOMOTIVE PROFILES.

General Information			
Uses	Automotive Applications		
	Profiles		
Appearance	lvory		
Processing Method	Profile Extrusion		
Physical	Nominal Value	Unit	Test Method
Density ¹	1.33 to 1.37	g/cm³	IEC 60811-1-3
Color	0.00OK		ME 12
Color a	-2.23 to 1.37		ME 12
Color b	1.27 to 4.87		ME 12
Color L	83.9 to 87.5		ME 12
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	83 to 87		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	> 12.7	MPa	IEC 60811-1-1
Tensile Strain (Yield)	> 250	%	IEC 60811-1-1
NOTE			
1.	24 hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533 Email: sales@su-jiao.com No. 215, Lianhe North Road, Fengxian District, Shanghai, China

