

PRL PC-FR3-D

Polycarbonate
Polymer Resources Ltd.

Message:

PRL PC-FR3-D is a Polycarbonate (PC) product. It can be processed by injection molding and is available in North America. Typical application: Outdoor Applications.
Characteristics include:
Flame Rated
RoHS Compliant
Flame Retardant
Heat Resistant
High Flow

General Information			
UL YellowCard	E113219-101708443		
Additive	Flame Retardant		
Features	Flame Retardant		
	High Flow		
	High Impact Resistance		
	Low Viscosity		
	Medium Heat Resistance		
	Self Extinguishing		
RoHS Compliance	RoHS Compliant		
UL File Number	E113219		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.21	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	14 to 20	g/10 min	ASTM D1238
Molding Shrinkage			ASTM D955
Flow : 3.18 mm	0.50 to 0.70	%	
Across Flow : 3.18 mm	0.50 to 0.70	%	
Outdoor Suitability	f1		UL 746C
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785
M-Scale	70		
R-Scale	118		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield, 3.18 mm	62.1	MPa	
Break, 3.18 mm	55.2	MPa	

Tensile Elongation			ASTM D638
Yield, 3.18 mm	7.0	%	
Break, 3.18 mm	90	%	
Flexural Modulus (3.18 mm)	2210	MPa	ASTM D790
Flexural Strength (3.18 mm)	89.6	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	640	J/m	ASTM D256
Gardner Impact (3.18 mm)	36.2	J	ASTM D3029
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 3.18 mm	135	°C	
1.8 MPa, Unannealed, 3.18 mm	129	°C	
Vicat Softening Temperature	149	°C	ASTM D1525 ¹
RTI Elec			UL 746
1.50 mm	125	°C	
3.00 mm	125	°C	
RTI Imp			UL 746
1.50 mm	110	°C	
3.00 mm	110	°C	
RTI Str			UL 746
1.50 mm	125	°C	
3.00 mm	125	°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+17	ohms · cm	ASTM D257
Dielectric Strength (1.50 mm)	23	kV/mm	ASTM D149
Arc Resistance (1.50 mm)	PLC 5		ASTM D495
Comparative Tracking Index (CTI) (1.50 mm)	PLC 2		UL 746
High Amp Arc Ignition (HAI)			UL 746
1.50 mm	PLC 0		
3.00 mm	PLC 0		
High Voltage Arc Tracking Rate (HVTR) (1.50 mm)	PLC 3		UL 746
Hot-wire Ignition (HWI)			UL 746
1.50 mm	PLC 2		
3.00 mm	PLC 2		
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.50 mm	V-0		

3.00 mm

5VA

Injection	Nominal Value	Unit
Drying Temperature	118 to 124	°C
Drying Time	3.0 to 4.0	hr
Drying Time, Maximum	8.0	hr
Rear Temperature	266 to 288	°C
Middle Temperature	277 to 299	°C
Front Temperature	288 to 310	°C
Processing (Melt) Temp	282 to 310	°C
Mold Temperature	71.1 to 93.3	°C
NOTE		

1. Rate B (120°C/h), Loading 2 (50 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

