

Karina BLACK PVC COMPOUND 860-48/1-AY-IS-BZ

Polyvinyl Chloride
Karina Ind. e Com. de Plásticos Ltda

Message:
HEAVY METAL FREE PVC COMPOUND RECOMMENDED FOR PROFILES EXTRUSION. ALSO RECOMMENDED FOR PLUG INJECTION.

General Information			
Uses	Reflectors		
Appearance	Black		
Processing Method	Injection Molding		
	Profile Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity ¹	1.30 to 1.36	g/cm ³	ASTM D792
Cadmium Content	< 50	ppm	IEC 62321
Chromium Content	< 100	ppm	IEC 62321
Color	OK		ME 12
Color a	-0.970 to 0.630		ME 12
Color b	-1.17 to 0.430		ME 12
Color L	26.0 to 27.6		ME 12
Mercury Content	< 100	ppm	IEC 62321
Bromine Content	< 100	ppm	IEC 62321
Lead Content	< 100	ppm	IEC 62321
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	86 to 90		NBR 7456
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	> 11.8	MPa	ASTM D638
Tensile Elongation (Yield)	> 200	%	ASTM D638
Flammability	Nominal Value		Test Method
Flame Rating	V-0		UL 94
NOTE			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

