

PENTAMID A GV30 H natur

Polyamide 66

PENTAC Polymer GmbH

Message:

Normal viscosity, heat stabilised polyamide 66, 30% glass fiber reinforced

General Information				
Filler / Reinforcement	Glass Fiber,30% Filler by Weight			
Additive	Heat Stabilizer			
Features	Heat Stabilized			
Uses	Housings			
Agency Ratings	EC 1907/2006 (REACH)			
Appearance	Natural Color			
Forms	Pellets			
Physical	Dry	Conditioned	Unit	Test Method
Density	1.36	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	0.70	--	%	
Flow	0.40	--	%	
Water Absorption				ISO 62
Saturation, 23°C	5.2	--	%	
Equilibrium, 23°C, 50% RH	1.6	--	%	
Viscosity Number	140	--	cm ³ /g	ISO 307
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness (H 961/30)	240	--	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	10000	7500	MPa	ISO 527-2/1
Tensile Stress (Break)	190	130	MPa	ISO 527-2
Tensile Strain (Break)	3.2	4.2	%	ISO 527-2
Flexural Modulus	8400	--	MPa	ISO 178
Flexural Stress	250	--	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	13	15	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	70	--	kJ/m ²	
23°C	85	95	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method

Heat Deflection Temperature				
0.45 MPa, Unannealed	255	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	240	--	°C	ISO 75-2/A
Melting Temperature	260	--	°C	ISO 11357-3
Electrical	Dry	Conditioned	Unit	Test Method
Electric Strength (1.00 mm)	35	--	kV/mm	IEC 60243-1
Relative Permittivity (1 MHz)	3.80	--		IEC 60250
Comparative Tracking Index	500	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
1.60 mm	HB	--		
3.20 mm	HB	--		
Additional Information	Dry	Conditioned		Test Method
ISO Type	PA66, MHR, 14-100, GF30	PA66, MHR, 14-100, GF30		ISO 1874
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Drying Time	3.0		hr	
Suggested Max Moisture	0.090		%	
Suggested Max Regrind	20		%	
Rear Temperature	265 to 290		°C	
Middle Temperature	280 to 295		°C	
Front Temperature	280 to 290		°C	
Processing (Melt) Temp	285		°C	
Mold Temperature	80.0		°C	
Injection Pressure	78.0		MPa	
Holding Pressure	46.8		MPa	
Screw L/D Ratio	20.0:1.0			
Screw Compression Ratio	2.2:1.0 to 2.8:1.0			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT