

SEPTON™ 2004

Styrene Ethylene Propylene Styrene Block Copolymer
Kuraray Co., Ltd.

Message:

SEPTON™ 2004 is a Styrene Ethylene Propylene Styrene Block Copolymer (SEPS) material. It is available in Asia Pacific, Europe, or North America.

General Information			
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	0.888	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	5.0	g/10 min	ISO 1133
Solution Viscosity - 15 wt% Toluene Solution (30°C)	150	mPa · s	
Styrene Content	18.0	wt%	
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	67		ISO 868
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	2.20	MPa	ISO 37
Tensile Stress (Yield)	16.0	MPa	ISO 37
Tensile Elongation (Break)	690	%	ISO 37

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China


WECHAT