

POCAN® BF 4235 000000

Polybutylene Terephthalate

LANXESS Asia/Pacific

Message:

PBT, 30 % glass fibers, injection molding, flame retardant

General Information			
UL YellowCard	E245249-101061124	E245249-522386	
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Additive	Flame retardancy		
Features	Flame retardancy		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
	1.66		
Density (23°C)	1.66	g/cm³	ISO 1183
Apparent Density	0.80	g/cm³	ISO 60
Melt Volume-Flow Rate (MVR) (260°C/2.16 kg)	24.0	cm³/10min	ISO 1133
Molding Shrinkage			ISO 2577
Vertical flow direction: 250°C, 2.00mm ¹	1.1	%	ISO 2577
Vertical flow direction: 120°C, 4 hours, 2.00mm ²	0.10	%	ISO 2577
Flow direction: 250°C, 2.00mm ³	0.40	%	ISO 2577
Flow direction: 120°C, 4 hours, 2.00mm ⁴	0.10	%	ISO 2577
Water Absorption			ISO 62
	0.40		
Saturated, 23°C	0.40	%	ISO 62
	0.10		
Equilibrium, 23°C, 50% RH	0.10	%	ISO 62
Viscosity Number (Reduced Viscosity)	93.0	ml/g	ISO 1628
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	210	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			

23°C	10900	MPa	ASTM D638
23°C	11000	MPa	ISO 527-2/1
Tensile Strength			
Fracture, 23°C	133	MPa	ASTM D638
Fracture, 23°C	135	MPa	ISO 527-2/5
Tensile Elongation			
Fracture, 23°C	1.8	%	ASTM D638
Fracture, 23°C	2.1	%	ISO 527-2/5
Tensile Creep Modulus			
1 hr	11000	MPa	ISO 899-1
1000 hr	10000	MPa	ISO 899-1
Flexural Modulus			
23°C	8550	MPa	ASTM D790
23°C ⁵	10500	MPa	ISO 178/A
Flexural Strength			
23°C	209	MPa	ASTM D790
23°C ⁶	210	MPa	ISO 178/A
Flexural Strain at Flexural Strength (23°C) ⁷	2.6	%	ISO 178/A
Halving Interval			
Electric Strength	12.4	°C	IEC 60216
Tensile Impact Strength	9.2	°C	IEC 60216
Tensile Strength	11.7	°C	IEC 60216
Temperature index			
Electric Strength, 20000 hr	145	°C	IEC 60216
Tensile Impact Strength, 20000 hr	135	°C	IEC 60216
Tensile Strength, 20000 hr	140	°C	IEC 60216
Electrolytical Corrosion (23°C)	A 1		IEC 60426
ISO Shortname	PBT, GFHMR, 07-110, GF30; ISO 1043-PBT GF FR (17)		ISO 7792
	0.0 - 0.020		
Residual Moisture Content	0.0	%	Karl Fisher
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	< 10	kJ/m ²	ISO 179/1eA
23°C	< 10	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	50	kJ/m ²	ISO 179/1eU
23°C	50	kJ/m ²	ISO 179/1eU
Notched Izod Impact			ISO 180/1A
-40°C	< 10	kJ/m ²	ISO 180/1A
-30°C	< 10	kJ/m ²	ISO 180/1A

23°C	< 10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength			ISO 180/1U
-30°C	45	kJ/m ²	ISO 180/1U
23°C	45	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	220	°C	ISO 75-2/B
1.8 MPa, not annealed	205	°C	ISO 75-2/A
Vicat Softening Temperature	210	°C	ISO 306/B120
Ball Pressure Test (215°C)	Pass		IEC 60695-10-2
Melting Temperature ⁸	225	°C	ISO 11357-3
Linear thermal expansion coefficient			ISO 11359-2
Flow: 23 to 55°C	2.0E-5	cm/cm/°C	ISO 11359-2
Lateral: 23 to 55°C	9.0E-5	cm/cm/°C	ISO 11359-2
Thermal Conductivity (23°C)	0.22	W/m/K	ISO 8302
RTI Elec	130	°C	UL 746
RTI Imp	130	°C	UL 746
RTI	140	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength (23°C, 1.00 mm)	29	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
23°C, 100 Hz	4.00		IEC 60250
23°C, 1 MHz	3.90		IEC 60250
Comparative Tracking Index (CTI)	PLC 2		UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.400 mm	V-0		UL 94
0.750 mm	V-0		UL 94
1.50 mm	V-0		UL 94
3.00 mm	V-0		UL 94
Glow Wire Flammability Index			IEC 60695-2-12
0.800 mm	960	°C	IEC 60695-2-12
1.50 mm	960	°C	IEC 60695-2-12
3.00 mm	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature			IEC 60695-2-13
0.750 mm	725	°C	IEC 60695-2-13
1.50 mm	725	°C	IEC 60695-2-13
3.00 mm	725	°C	IEC 60695-2-13
Oxygen Index ⁹	32	%	ISO 4589-2
Injection	Nominal Value	Unit	Test Method
Drying Temperature - Circulation Dryer	120	°C	

4.0 - 8.0

Drying Time - Circulation Dryer	4.0	hr
Processing (Melt) Temp	240 - 260	°C
Mold Temperature	80.0 - 100	°C

NOTE

1.	60x60x2mm, 80°C MT, 600 bar
2.	60x60x2mm
3.	60x60x2mm, 80°C MT, 600 bar
4.	60x60x2mm
5.	2.0 mm/min
6.	2.0 mm/min
7.	2 mm/min
8.	10°C/min
9.	Procedure A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

