Polyrocks EP8400X105V-2

Crosslinked Polyethylene

Polyrocks Chemical Co., Ltd

Message:

Irradiation cross-linked low-smoke halogen-free flame retardant polyolefin wire & cable compound is environmental flame retardant material with hydroxide as main flame retardant elements. Dehydration endothermic and carbonize play the flame retardant performance. Irradiation cross-linked low-smoke halogen-free flame retardant polyolefin wire & cable compound, which Mechanical properties meet the requirements of XLPE coating of electronic wire, automotive wire and photovoltaic wire, flammability reach UL1581 VW-1, and meet the requirements of ROHS, SVHC, PFOS & PFOA, 16P, Halogen, PAHs... etc.

| General Information | | |
|--|----------------------------------|-------|
| Additive | Flame retardancy 2 | |
| Features | Low smoke | |
| | Radiation crosslinkable | |
| | Halogen-free | |
| | Flame retardancy | |
| | | |
| Uses | Wire and cable applications | |
| | Wire sheath | |
| | Electronic cable sheath material | |
| Wire Types | VW-1 | |
| Agency Ratings | EC 1907/2006 (REACH) | |
| RoHS Compliance | RoHS compliance | |
| Forms | Particles | |
| Physical | Nominal Value | Unit |
| Density | 1.68 | g/cm³ |
| рН | 5.5 | |
| Toxicity | 1.20 | |
| Smoke Density | | |
| Flame | 52 | |
| Flameless | 130 | |
| Electrical Conductivity | 1.20 | μS/mm |
| Halogen Acid Gas Evolution | 0.00 | mg/g |
| Mechanical | Nominal Value | Unit |
| Tensile Strength | 11.0 | MPa |
| Tensile Elongation (Break) | 170 | % |
| Aging | Nominal Value | Unit |
| Change in Tensile Strength in Air (136°C, 168 hr) | -4.0 | % |
| Change in Ultimate Elongation in Air (136°C, 168 hr) | -15 | % |

| Thermal | Nominal Value | Unit |
|---------------------------|---------------|---------|
| Brittleness Temperature | -40.0 | °C |
| Electrical | Nominal Value | Unit |
| Volume Resistivity (20°C) | 1.2E+14 | ohms·cm |
| Dielectric Strength | 25 | kV/mm |
| Flammability | Nominal Value | Unit |
| Oxygen Index | 45 | % |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

