

Ultradur® B 4300 G2 FC

Polybutylene Terephthalate

BASF Corporation

Message:

Ultradur B 4300 G2 FC is a easy flowing injection molding food contact PBT with 10% glass fiber reinforcement for rigid, tough, and dimensionally stable parts.

General Information			
Filler / Reinforcement	Glass Fiber,10% Filler by Weight		
Features	Food Contact Acceptable		
	Good Dimensional Stability		
	Good Flow		
	Good Toughness		
	High Rigidity		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.37	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (250°C/2.16 kg)	16.0	cm³/10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	1.4	%	
Flow	1.2	%	
Water Absorption			ISO 62
Saturation, 23°C	0.40	%	
Equilibrium, 23°C, 50% RH	0.20	%	
Viscosity Number (Reduced Viscosity)	115.0	ml/g	ISO 1628
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	4500	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	85.0	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	4.5	%	ISO 527-2
Flexural Stress (23°C)	140	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	4.0	kJ/m²	ISO 179
Charpy Unnotched Impact Strength			ISO 179
-30°C	38	kJ/m²	
23°C	40	kJ/m²	
Thermal	Nominal Value	Unit	Test Method

Heat Deflection Temperature			
0.45 MPa, Unannealed	220	°C	ISO 75-2/B
1.8 MPa, Unannealed	200	°C	ISO 75-2/A
Melting Temperature (DSC)	223	°C	ISO 3146
CLTE - Flow	4.5E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13	ohms	IEC 60093
Volume Resistivity	1.0E+14	ohms·cm	IEC 60093
Dielectric Constant			IEC 60250
100 Hz	3.60		
1 MHz	3.60		
Dissipation Factor			IEC 60250
100 Hz	1.2E-3		
1 MHz	0.015		
Comparative Tracking Index	300	V	IEC 60112
Injection	Nominal Value	Unit	
Drying Temperature	100 to 120	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.040	%	
Processing (Melt) Temp	250 to 270	°C	
Mold Temperature	60.0 to 100	°C	
Injection Pressure	3.45 to 10.3	MPa	
Injection Rate	Fast		
Back Pressure	< 1.00	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

