

TABOREN PR 79 T 30

Polypropylene Copolymer

SILON s.ro

Message:

TABOREN PR 79 T 30 is a Polypropylene Copolymer (PP Copolymer) product filled with 30% talc. It is available in Asia Pacific or Europe. Typical application: Automotive.

Characteristics include:

Antioxidant

Copolymer

Good UV Resistance

Impact Modified

UV Stabilized

General Information			
Filler / Reinforcement	Talc,30% Filler by Weight		
Additive	Antioxidant		
	Rubber Impact Modifier		
	UV Stabilizer		
Features	Antioxidant		
	Copolymer		
	Good UV Resistance		
	Impact Modified		
Uses	Automotive Applications		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	24.0	MPa	ISO 527-2/1B/50
Tensile Strain (Yield)	30	%	ISO 527-2
Flexural Modulus	2500	MPa	ISO 178
Flexural Stress	33.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	20	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	95	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	140	°C	ISO 306/A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT