

Latigray 82-05 CX/90

Polyamide 12

LATI S.p.A.

Message:

Radiopaque compound based on Polyamide 12 (PA 12). Metallic filler.

General Information			
Filler / Reinforcement	Metallic,90% Filler by Weight		
Features	Radiopaque		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	4.26	g/cm ³	ISO 1183
Molding Shrinkage ¹			ISO 294-4
Across Flow : 2.00 mm	0.70 to 0.90	%	
Flow : 2.00 mm	0.70 to 0.90	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	9700	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	35.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	0.70	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ² (23°C)	5.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength ³ (23°C)	15	kJ/m ²	ISO 179/1eU
Notched Izod Impact ⁴ (23°C)	55	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	160	°C	ISO 75-2/B
1.8 MPa, Unannealed	95.0	°C	ISO 75-2/A
Vicat Softening Temperature	165	°C	ISO 306/B50
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	5.0E+3	ohms	ASTM D257
Volume Resistivity	7.0E+3	ohms · cm	ASTM D257
Electromagnetic Reflection	74	%	ASTM EST-83
Half Value Thickness			Internal Method
-- ⁵	660.0	µm	
-- ⁶	340.0	µm	
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 100	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	250 to 270	°C	

Mold Temperature	60.0 to 80.0	°C
Injection Rate	Moderate	
NOTE		
1.	at 60 Mpa of cavity pressure	
2.	80x10x4 mm	
3.	80x10x4 mm	
4.	63.5x12.7x3.2 mm	
5.	120 kV	
6.	80 kV	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

