

ADEKA EP-4100E

Epoxy; Epoxide
Adeka Corporation

Message:
Low saponifiable chlorine product
Electrics, laminated plates, cast molding

General Information		
Uses	Electrical/Electronic Applications	
	Laminates	
Processing Method	Casting	
Physical	Nominal Value	Unit
Specific Gravity	1.16	g/cm ³
Chlorine Content - Saponifiable	0.0100	wt%
Color - G, Max	1.0	
Epoxy Equivalent	190 g/ep	
Thermoset	Nominal Value	Unit
Thermoset Mix Viscosity (25°C)	13000	cP

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT