Paraclean® 28L80

Acrylonitrile Butadiene Rubber

INSA

Message:

Description: Fast curing. Excellent low temperature flexibility with moderate oil resistance. Low water absorption. Low corrosion. Cold polymerized. Non staining stabilizer Applications: Sponge, extrusions. O-rings, seals, gaskets, grommets, and diaphragms. Hose and tubes requiring low temperature flexibility.

| General Information | | | |
|----------------------------------|-----------------------------|-------|-----------------|
| Features | Fast Cure | | |
| | Low Temperature Flexibility | | |
| | Low to No Water Absorption | | |
| | Stain Resistant | | |
| | | | |
| Uses | Diaphragms | | |
| | Gaskets | | |
| | Grommets | | |
| | Hose | | |
| | Seals | | |
| | Tubing | | |
| | | | |
| Processing Method | Extrusion | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 0.970 | g/cm³ | ASTM D297 |
| Mooney Viscosity (ML 1+4, 100°C) | 73 to 87 | MU | ASTM D1646 |
| ACN Content - Bound | 26.5 to 29.5 | wt% | Internal Method |
| Ash Content | < 0.8 | wt% | ASTM D5667 |
| Volatile Matter | < 1.0 | wt% | ASTM D5668 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

