

Crastin® HR5330HFS NC010

THERMOPLASTIC POLYESTER RESIN

DuPont Performance Polymers

Message:

30% Glass Reinforced Polybutylene Terephthalate with Improved Processing

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Mold Release		
Forms	Pellets		
Processing Method	Injection Molding		
Multi-Point Data	Isothermal Stress vs. Strain (ISO 11403-1)		
	Secant Modulus vs. Strain (ISO 11403-1)		
	Shear Stress vs. Shear Rate (ISO 11403-1)		
	Tensile Modulus vs. Temperature (ISO 11403-1)		
	Viscosity vs. Shear Rate (ISO 11403-2)		
Part Marking Code (ISO 11469)	>PBT-IGF30<		
Resin ID (ISO 1043)	PBT-IGF30		
Physical	Nominal Value	Unit	Test Method
Density	1.50	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (250°C/2.16 kg)	7.50	cm³/10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	1.0	%	
Flow	0.30	%	
Water Absorption			ISO 62
23°C, 24 hr, 2.00 mm	0.35	%	
Equilibrium, 23°C, 2.00 mm, 50% RH	0.15	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	8500	MPa	ISO 527-2
Tensile Stress (Break)	130	MPa	ISO 527-2
Tensile Strain (Break)	3.1	%	ISO 527-2
Flexural Stress	195	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-40°C	10	kJ/m²	
23°C	13	kJ/m²	
Charpy Unnotched Impact Strength (23°C)	70	kJ/m²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method

Heat Deflection Temperature			
0.45 MPa, Unannealed	222	°C	ISO 75-2/B
1.8 MPa, Unannealed	207	°C	ISO 75-2/A
Glass Transition Temperature ¹	65.0	°C	ISO 11357-2
Melting Temperature ²	225	°C	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms·cm	IEC 60093
Electric Strength	34	kV/mm	IEC 60243-1
Comparative Tracking Index	575	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Burning Rate (1.00 mm)	30	mm/min	ISO 3795
Flammability Classification (1.50 mm)	HB		IEC 60695-11-10, -20
Oxygen Index	20	%	ISO 4589-2
Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (250°C, 1000 sec ⁻¹)	230	Pa·s	ISO 11443
NOTE			
1.	10°C/min		
2.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT