

Sicoklar E71.15

Polycarbonate
Ravago Group

Message:

PC, V0 flame retardant grade also available in transparent colors

General Information			
Additive	Flame Retardant		
Features	Flame Retardant		
Appearance	Clear/Transparent		
	Colors Available		

Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	15	g/10 min	ISO 1133
Molding Shrinkage	0.50 to 0.70	%	ISO 2577

Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-2
Yield	60.0	MPa	
Break	55.0	MPa	
Tensile Strain (Break)	50	%	ISO 527-2
Flexural Modulus	2400	MPa	ISO 178

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ISO 180/1A
-30°C	10	kJ/m ²	
23°C	50	kJ/m ²	

Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Annealed)	133	°C	ISO 75-2/A
Vicat Softening Temperature			
--	146	°C	ISO 306/A50
--	140	°C	ISO 306/B50
Ball Pressure Test (125°C)	Pass		

Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms · cm	IEC 60093
Electric Strength (1.00 mm, in Oil)	17	kV/mm	IEC 60243-1
Comparative Tracking Index	225	V	IEC 60112

Flammability	Nominal Value	Unit	Test Method
Flame Rating ¹	Internal Method		

0.750 mm	V-2		
1.60 mm	V-2		
3.20 mm	V-0		
Glow Wire Flammability Index (2.00 mm)	960	°C	IEC 60695-2-12
NOTE			
1.	UL94 internally tested		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT