

Sylvin 9788F1 Black

Polyvinyl Chloride
Sylvin Technologies Incorporated

Message:

Sylvin 9788F1 Black Is A Vinyl Compound Formulated For Injection Molding Applications That Meet The Requirements Of Ford ESB-M4D317-A Type 1, But Is Not On The Ford Approval List.

General Information			
Uses	Application in Automobile Field		
Appearance	Black		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.21	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shaw A	50		ASTM D2240
Shaw A, 10 seconds	50		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	8.27	MPa	ASTM D638
Tensile Elongation (Break)	480	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Tear Strength	28.0	kN/m	ASTM D624
Thermal	Nominal Value	Unit	
Melting Temperature	149 - 166	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT