

# K PP 11000

Compounded Polypropylene

Technovinyl Polymers India Ltd.

## Message:

K PP 11000 is a Compounded Polypropylene material. It is available in Africa & Middle East.

Important attributes of K PP 11000 are:

Impact Resistant

Good UV Resistance

High Flow

High Shrinkage

Typical application of K PP 11000: Automotive

General Information			
Features	Good UV Resistance		
	High Flow		
	High Impact Resistance		
	High Shrinkage		
	Low Temperature Impact Resistance		
Uses	Automotive Bumper		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.920 to 0.940	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	> 14	g/10 min	ASTM D1238
Molding Shrinkage - Flow	< 1.0	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	52		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	18.6	MPa	ASTM D638
Flexural Modulus	1370	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-20°C	98	J/m	
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	140	°C	ASTM D1525

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

