Precision Polymer V71C

Fluoroelastomer

Precision Polymer Engineering Ltd.

Message:

V71C is a Terpolymer FKM material developed to offer increased efficiency and service life in low temperature applications.

V71C extends the operational performance of FKM seals by a full 15°C lower than is possible with well established low temperature FKM grades. It sets a new industry benchmark in low temperature performance.

V71C exhibits the same chemical and mechanical properties as B-type and G-type FKM grades.

Available in any sized O-ring (fully moulded up to 2m/6.5ft internal diameter) and custom designed components.

Key Attributes

With a glass transition of -40°C (-40°F), V71C offers the widest operating temperature range of -51°C to +225°C

Low compression set giving excellent seal performance

Good elongation properties making fitting easier even at low temperature

Excellent resistance to petroleum, oil, silicone and di-ester liquids

Typical Applications

Valves and pumps in cold (Arctic) operating environments

Mechanical seals

Flow meters & sensors

Seal applications that are exposed to cold situations or high temperature variations.

General Information			
Features	Low compressive deformability		
	Low temperature resistance		
	Oil resistance		
Uses	Pump parts		
	Low temperature application		
	Valve/valve components		
	Seals		
Appearance	Black		
Hardness	Nominal Value		Test Method
IRHD Hardness	72		ASTM D1415, ISO 48
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	13.0	MPa	ASTM D412, ISO 37
Tensile Elongation (Break)	180	%	ASTM D412, ISO 37
Compression Set (200°C, 24 hr)	18	%	ASTM D395, ISO 815
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air (250°C, 72 hr)	-30	%	ASTM D412, ISO 37
Change in Ultimate Elongation in Air (250°C, 72 hr)	30	%	ASTM D412, ISO 37
Change in IRHD Hardness in Air (250°C, 72 hr)	-7.0		ASTM D573, ISO 188
Thermal	Nominal Value	Unit	
Glass Transition Temperature	-40.0	°C	

Maximum Operating Temperature

225

°C

Additional Information

Minimum Operating Temperature: -51°C (-60°F)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

