

Prime Polypro™ J-3021GR

Polypropylene Random Copolymer

Prime Polymer Co., Ltd.

Message:

Prime Polypro™ J-3021GR is a Polypropylene Random Copolymer (PP Random Copolymer) product. It can be processed by injection molding and is available in Asia Pacific, Europe, or North America.

Characteristics include:

Antistatic

Copolymer

General Information			
Additive	Antistatic		
Features	Antistatic		
	Random Copolymer		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	33	g/10 min	ISO 1133
Molding Shrinkage	1.4 to 1.8	%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	76		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1000	MPa	ISO 527-2
Tensile Stress (Yield)	27.0	MPa	ISO 527-2
Tensile Strain (Break)	17	%	ISO 527-2
Nominal Tensile Strain at Break	200	%	ISO 527-2
Flexural Modulus	1000	MPa	ISO 178
Flexural Stress	31.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength (23°C)	5.5	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	78.0	°C	ISO 75-2/B
Optical	Nominal Value	Unit	Test Method
Haze (2000 μm)	33	%	ISO 14782

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

