

Vyncolit® RX®2-520

Diallyl Phthalate

Vyncolit N.V.

Message:

Vyncolit RX®2-520 is a diallyl phthalate (DAP) material, and the filler is glass fiber reinforced material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. The processing methods are: resin transfer molding, compression molding or injection molding.

Vyncolit RX®The main features of 2-520 are:

flame retardant/rated flame

chemical resistance

Good dimensional stability

moisture resistance

Impact resistance

Typical application areas include:

Electrical/electronic applications

Wire and cable

Aerospace

military applications

General Information	
Filler / Reinforcement	Glass fiber reinforced material
Features	Good dimensional stability
	Moisture resistance
	Antibacterial property
	Solvent resistance
	Impact resistance, high
	Good electrical performance
	Good chemical resistance
	alkali resistance
	Good wear resistance
	Fuel resistance
	Heat resistance, high
	acid resistance
Uses	Membrane key switch
	Aircraft applications
	Insulating material
	Connector
	Communication Equipment
Agency Ratings	MIL C-24308
Forms	Particles
Processing Method	Resin transfer molding
	Compression molding

Injection molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.75	g/cm ³	ASTM D792
Bulk Factor	2.5		ASTM D1895
Molding Shrinkage - Flow (Compression Molded)	0.10 - 0.30	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	77.2	MPa	ASTM D638
Flexural Modulus	12400	MPa	ASTM D790
Flexural Strength	55.2	MPa	ASTM D790
Compressive Strength	152	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	43	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	274	°C	ASTM D648
CLTE - Flow	1.8E-5	cm/cm/°C	ASTM D696
RTI Elec	130	°C	UL 746
RTI Imp	130	°C	UL 746
RTI	130	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength			ASTM D149
-- ¹	18	kV/mm	ASTM D149
-- ²	16	kV/mm	ASTM D149
Dielectric Constant			ASTM D150
1 kHz	3.90		ASTM D150
1 MHz	3.70		ASTM D150
Dissipation Factor			ASTM D150
1 kHz	0.011		ASTM D150
1 MHz	0.015		ASTM D150
Arc Resistance	150	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.59 mm	HB		UL 94
3.18 mm	HB		UL 94
Oxygen Index	25	%	ASTM D2863
Injection	Nominal Value	Unit	
Rear Temperature	60.0	°C	
Middle Temperature	76.7	°C	
Nozzle Temperature	87.8	°C	
Processing (Melt) Temp	110 - 116	°C	
Mold Temperature	160 - 182	°C	

Injection instructions

Plastication: 50rpm Back Pressure (gauge): slight Injection Pressure: set to give 5 to 15 sec injection time Hold Pressure: 1/2 of injection pressure Cure Time, 0.125 in: 40 sec Resin Isomer, DAP: ISO Water Absorption, ASTM D570, 48 hrs, 50°C: 0.25% Dielectric Strength, ASTM D149, 60 Hz, Method A, wet: 450 V/mil Dielectric Strength, ASTM D149, 60 Hz, Method B, wet: 400 V/mil Dielectric Constant, ASTM D150, 1000 Hz, wet: 3.9 Dielectric Constant, ASTM D150, 1000000 Hz, wet: 3.7 Dissipation Factor, ASTM D150, 1000 Hz, wet: 0.011 Dissipation Factor, ASTM D150, 1000000 Hz, wet: 0.015 Compression and Transfer Molding Conditions:
Preforming Pressure: 8000 to 12000 psi
Preheat Temperature: 220 to 230 °F
Preheat Time: 45 sec
Mold Temperature: 320 to 350 °F
Compression Mold Pressure: 3500 to 6000 psi
Transfer Mold Pressure: 2500 to 5000 psi
Cure Time, 0.125 in: 45 to 70 sec

NOTE

- | | |
|----|-------------------------|
| 1. | Method A (short time) |
| 2. | Method B (step by step) |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

