

Axiall PVC 38511

Flexible Polyvinyl Chloride

Axiall Corporation

Message:

Tray cable jacket with excellent low temperature properties.

General Information			
Uses	Cable Jacketing		
	Wire & Cable Applications		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.36	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 10 sec)	82 to 88		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	17.2	MPa	ASTM D638
Tensile Elongation (Break)	320	%	ASTM D638
Aging	Nominal Value	Unit	Test Method
Change in Ultimate Elongation in Air ¹ (121°C, 168 hr)	-20	%	UL 1581
Change in Ultimate Elongation (70°C, 4 hr, in Oil)	-18	%	UL 1581
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-45.6	°C	ASTM D746
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	32	%	ASTM D2863
Extrusion	Nominal Value	Unit	
Melt Temperature	182	°C	
NOTE			

1. 75 mil plaque

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT