

Promyde® B33 UV

Polyamide 6

NUREL, S.A.

Message:

Promyde® B33UV is a Polyamide 6 grade of medium viscosity with UV protection. The polymer is suitable for all type of extrusion applications like the production of high tenacity yarns.

General Information			
Features	Good UV Resistance		
	Medium Viscosity		
Uses	High Tenacity Flat Yarn		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm ³	ISO 1183
Apparent Density ¹	0.69	g/cm ³	Internal Method
Moisture Content ²	< 0.10	%	Internal Method
Relative Viscosity	3.21 to 3.41		ISO 1628
Chip Size ³	2.50	mm	Internal Method
Monomers	< 0.60	%	ISO 599
Thermal	Nominal Value	Unit	Test Method
Melting Temperature (DSC)	220	°C	ISO 3146
NOTE			
1.	NAPPA-059		
2.	NAPPA-032		
3.	NAPPA-045		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT