

LEXAN™ XHT4141 resin

Polycarbonate

SABIC Innovative Plastics

Message:

XHT4141 is a high flow, high heat polycarbonate copolymer. It is available in a range of opaque and limited transparent colors.

General Information			
UL YellowCard	E207780-100025118		
Features	Copolymer		
	High liquidity		
	Heat resistance, high		
Appearance	Opacity		
	Clear/transparent		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.20	g/cm ³	ASTM D792
--	1.21	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (330°C/2.16 kg)	25	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (330°C/2.16 kg)	24.0	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.60 - 0.95	%	Internal method
Water Absorption			ISO 62
Saturated, 23°C	0.50	%	ISO 62
Equilibrium, 23°C, 50% RH	0.25	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2730	MPa	ASTM D638
--	2750	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	77.0	MPa	ASTM D638
Yield	78.0	MPa	ISO 527-2/50
Fracture ³	69.0	MPa	ASTM D638
Fracture	67.0	MPa	ISO 527-2/50
Tensile Elongation			
Yield ⁴	7.0	%	ASTM D638
Yield	7.0	%	ISO 527-2/50
Fracture ⁵	50	%	ASTM D638

Fracture	50	%	ISO 527-2/50
Flexural Modulus			
50.0mm span ⁶	2600	MPa	ASTM D790
-- ⁷	2600	MPa	ISO 178
Flexural Stress			
--	80.0	MPa	ISO 178
Yield, 50.0mm span ⁸	120	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹			ISO 179/1eA
-30°C	9.0	kJ/m ²	ISO 179/1eA
23°C	11	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength ¹⁰			ISO 179/1eU
-30°C	No Break		ISO 179/1eU
23°C	No Break		ISO 179/1eU
Notched Izod Impact			
-30°C	76	J/m	ASTM D256
23°C	93	J/m	ASTM D256
-30°C ¹¹	8.0	kJ/m ²	ISO 180/1A
23°C ¹²	10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ¹³			ISO 180/1U
-30°C	No Break		ISO 180/1U
23°C	No Break		ISO 180/1U
Instrumented Dart Impact (23°C, Total Energy)	72.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 3.20mm	174	°C	ASTM D648
0.45 MPa, unannealed, 64.0mm span ¹⁴	173	°C	ISO 75-2/Bf
1.8 MPa, unannealed, 3.20mm	165	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ¹⁵	162	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	183	°C	ASTM D1525, ISO 306/B50 11 ¹⁶
--	181	°C	ISO 306/B120
Ball Pressure Test			IEC 60695-10-2
125°C	Pass		IEC 60695-10-2
165°C	Pass		IEC 60695-10-2
Linear thermal expansion coefficient			ASTM E831, ISO 11359-2
Flow: -40 to 40°C	6.0E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Lateral: -40 to 40°C	6.0E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Thermal Conductivity (25°C)	0.20	W/m/K	ASTM C177
RTI Elec	150	°C	UL 746
RTI Imp	130	°C	UL 746

RTI	150	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+17	ohms	ASTM D257
Volume Resistivity	> 1.0E+17	ohms·cm	ASTM D257
Dielectric Constant			ASTM D150
100 Hz	3.12		ASTM D150
1 MHz	3.02		ASTM D150
High Amp Arc Ignition (HAI)	PLC 0		UL 746
Hot-wire Ignition (HWI)	PLC 3		UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.50 mm	HB		UL 94
3.00 mm	HB		UL 94
Glow Wire Flammability Index (3.00 mm)	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (3.00 mm)	875	°C	IEC 60695-2-13
Additional Information	Nominal Value	Unit	Test Method
Metallized Haze Onset	175	°C	Internal method
Injection	Nominal Value	Unit	
Drying Temperature	135	°C	
Drying Time	4.0 - 6.0	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	40 - 60	%	
Rear Temperature	280 - 315	°C	
Middle Temperature	290 - 335	°C	
Front Temperature	300 - 345	°C	
Nozzle Temperature	285 - 325	°C	
Processing (Melt) Temp	300 - 345	°C	
Mold Temperature	95.0 - 130	°C	
Back Pressure	0.300 - 0.700	MPa	
Screw Speed	40 - 90	rpm	
Vent Depth	0.025 - 0.080	mm	
NOTE			
1.	5.0 mm/min		
2.	Type 1, 50mm/min		
3.	Type 1, 50mm/min		
4.	Type 1, 50mm/min		
5.	Type 1, 50mm/min		
6.	1.3 mm/min		
7.	2.0 mm/min		
8.	1.3 mm/min		
9.	80*10*3 sp=62mm		
10.	80*10*3 sp=62mm		

11.	80*10*3
12.	80*10*3
13.	80*10*3
14.	80*10*4 mm
15.	80*10*4 mm
16.	标准 B (120°C/h), 载荷2 (50N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT