

MAXAMID™ PA66G50HSL-BK

Polyamide 66
Pier One Polymers, Inc.

Message:
MAXAMID™ PA66G33 is available in natural or black, internal and external lubricants, UV stabilized and other modifications. Further information and details are available upon request.

| General Information | | | |
|---|---|-------------------|-------------|
| Filler / Reinforcement | Glass fiber reinforced material, 50% filler by weight | | |
| Additive | heat stabilizer | | |
| | Lubricant | | |
| | UV stabilizer | | |
| Features | UV Stabilized | | |
| | Thermal Stability | | |
| | Lubrication | | |
| Appearance | Black | | |
| | Natural color | | |
| Forms | Particle | | |
| Processing Method | Injection molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.56 | g/cm ³ | ASTM D792 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength (23°C) | 228 | MPa | ASTM D638 |
| Tensile Elongation (Break, 23°C) | 3.0 | % | ASTM D638 |
| Flexural Modulus (23°C) | 15900 | MPa | ASTM D790 |
| Flexural Strength (23°C) | 304 | MPa | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact (23°C) | 160 | J/m | ASTM D256 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (1.8 MPa, Unannealed) | 250 | °C | ASTM D648 |
| Peak Melting Temperature | 259 | °C | ASTM D3418 |
| Injection | Nominal Value | Unit | |
| Suggested Max Moisture | 0.20 | % | |
| Processing (Melt) Temp | 290 - 305 | °C | |
| Mold Temperature | 65 - 120 | °C | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

