

Huaфон JF-S-AH8060

Polyurethane
Huaфон Group Co., Ltd.

Message:

Cold Resistance Type
Characteristics
Mid hard type, cold resistance, hydrolysis resistance, solvent resistance, swelling resistance, good solubility with pigment.
Applications
Micro fibre, Shoes, Bags

General Information	
Features	Hydrolysis Resistant
	Low Temperature Resistant
	Medium Hardness
	Solvent Resistant
Uses	Bags
	Footwear

Additional Information	Nominal Value	Unit
Solvents	DMF/MEK	
Uncured Properties	Nominal Value	Unit
Solids Content	29 to 31	%
Viscosity (25°C)	80 to 140	Pa·s
Cured Properties	Nominal Value	Unit
Tensile Modulus (100% Secant)	5.50 to 6.50	MPa
Tensile Strength	> 40.0	MPa
Tensile Elongation at Break	> 500	%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT