# YUNGSOX® PP 2100M

### Polypropylene Homopolymer

### Formosa Polypropylene

#### Message:

YUNGSOX® PP 2100M is a Polypropylene Homopolymer (PP Homopolymer) material. It is available in Asia Pacific. Important attributes of YUNGSOX® PP 2100M are: Clarity Homopolymer Typical applications include: Film Coating Applications Food Contact Applications

General Information			
Features	High Clarity		
	Homopolymer		
Uses	Cast Film		
	Film		
	Laminates		
Agency Ratings	FDA 21 CFR 177.1520		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16			
kg)	7.0	g/10 min	ISO 1133
Molding Shrinkage	1.3 to 1.7	%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	107		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	34.3	MPa	ISO 527-2
Tensile Strain (Break)	500	%	ISO 527-2
Flexural Modulus	1370	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	44	J/m	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	115	°C	ISO 75-2/A
Vicat Softening Temperature	155	°C	ISO 306
Melting Temperature	165	°C	DSC
Optical	Nominal Value	Unit	Test Method
Haze (30.0 µm)	< 0.50	%	Internal Method

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

