

HONES® PBT GF30B

Polybutylene Terephthalate

Guangdong Shunde Hones Polymer Material Co., Ltd.

Message:

Technology characteristics: 30% glass fiber reinforced, flame retardant, low precipitation

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Flame Retardant		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.60	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.40 to 0.90	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.080	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	110	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	7000	MPa	ASTM D790
Flexural Strength	160	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	7.0	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	38	kJ/m ²	ISO 179
Unnotched Izod Impact (3.20 mm)	69	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	200	°C	ASTM D648
CLTE - Flow (-30 to 30°C)	2.5E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms · cm	ASTM D257
Dielectric Constant (1 MHz)	3.30		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating (3.20 mm)	V-0		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

