

Fenochem C 3500

Phenolic

Chemiplastica, Inc.

Message:

Colour : black

Reinforcement : wood flour/inorganic

Application areas : for general purpose, easy to mould, suitable for the production of a wide range of articles

Mark : DIN 31/1449

General Information			
Filler / Reinforcement	Wood Flour\Inorganic		
Features	General Purpose		
	Good Moldability		
	Renewable Resource Content		
Uses	General Purpose		
Appearance	Black		
Processing Method	Compression Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.40	g/cm ³	ISO 1183
Molding Shrinkage			ISO 2577
-- ¹	0.40 to 0.60	%	
--	0.60 to 0.80	%	
Water Absorption	< 100.0	mg	ISO 62
Flammability	< BH 2-10		IEC 707
Mechanical	Nominal Value	Unit	Test Method
Flexural Stress	> 100	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	> 1.3	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	> 4.5	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	> 115	°C	ISO 75-2/A
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+8	ohms	IEC 60093
Volume Resistivity	> 1.0E+10	ohms · cm	IEC 60093
Comparative Tracking Index	> 125	V	IEC 60112
NOTE			
1.	Post-shrink		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT