

Durethan® BM 25 FN20 700350

Polyamide 6

LANXESS Asia/Pacific

Message:

PA 6, 25 % mineral, injection molding, halogen free flame retardant

General Information				
UL YellowCard		E245249-550630		
Filler / Reinforcement		Mineral,25% Filler by Weight		
Additive		Flame Retardant		
Features		Flame Retardant		
		Halogen Free		
Agency Ratings		EC 1907/2006 (REACH)		
Processing Method		Injection Molding		
Resin ID (ISO 1043)		PA MD FR (30)		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.38	--	g/cm ³	ISO 1183
Apparent Density	0.70	--	g/cm ³	ISO 60
Molding Shrinkage				ISO 2577
Across Flow : 280°C, 2.00 mm ¹	0.90	--	%	
Across Flow : 120°C, 4 hr, 2.00 mm ²	0.20	--	%	
Flow : 280°C, 2.00 mm ³	0.90	--	%	
Flow : 120°C, 4 hr, 2.00 mm ⁴	0.20	--	%	
Water Absorption (Saturation, 23°C)	6.7	--	%	ISO 62
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness	178	70.0	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	5700	2100	MPa	ISO 527-2/1
Tensile Stress				
Yield, 23°C	80.0	30.0	MPa	ISO 527-2/50
Break, 23°C	80.0	30.0	MPa	ISO 527-2/5
Tensile Strain				
Yield, 23°C	3.0	8.0	%	ISO 527-2/50
Break, 23°C	3.0	7.0	%	ISO 527-2/5
Flexural Modulus ⁵ (23°C)	5500	2000	MPa	ISO 178/A
Flexural Stress				ISO 178/A

3.5% Strain,23°C	130	43.0	MPa	
23°C ⁶	135	50.0	MPa	
Flexural Strain at Flexural Strength ⁷ (23°C)	3.5	6.8	%	ISO 178/A
ISO Shortname	PA 6, GFHR, 14-060, MD25	--		ISO 1874
Residual Moisture Content	0.030 to 0.070		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method
Charpy Unnotched Impact Strength (23°C)	38	140	kJ/m ²	ISO 179/1eU
Notched Izod Impact Strength (23°C)	< 10	< 10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength (23°C)	30	100	kJ/m ²	ISO 180/1U
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	195	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	90.0	--	°C	ISO 75-2/A
Vicat Softening Temperature				
--	205	--	°C	ISO 306/B50
--	206	--	°C	ISO 306/B120
Ball Pressure Test (205°C)	Pass	--		IEC 60695-10-2
Melting Temperature ⁸	220	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow : 23 to 55°C	6.0E-5	--	cm/cm/°C	
Transverse : 23 to 55°C	7.0E-5	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Comparative Tracking Index (CTI)	PLC 1	--		UL 746
Comparative Tracking Index (Solution A)	450	--	V	IEC 60112
High Amp Arc Ignition (HAI)	PLC 0	--		UL 746
	PLC 2			
	PLC 3			
Hot-wire Ignition (HWI)	PLC 4	--		UL 746
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.750 mm	V-2	--		
1.50 mm	V-2	--		
3.00 mm	V-2	--		

Glow Wire Flammability Index				IEC 60695-2-12
0.800 mm	960	--	°C	
1.50 mm	960	--	°C	
3.00 mm	960	--	°C	
Glow Wire Ignition Temperature				IEC 60695-2-13
0.750 mm	725	--	°C	
1.50 mm	725	--	°C	
3.00 mm	725	--	°C	
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 to 6.0		hr	
Processing (Melt) Temp	250 to 270		°C	
Mold Temperature	80.0 to 100		°C	
NOTE				
1.	60x60x2mm, 80°C MT, 600 bar			
2.	60x60x2mm			
3.	60x60x2mm, 80°C MT, 600 bar			
4.	60x60x2mm			
5.	2.0 mm/min			
6.	2.0 mm/min			
7.	2 mm/min			
8.	10°C/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT