

DOMAMID® 6G50AFHUV

Polyamide 6

DOMO Engineering Plastics SPA

Message:

Polyamide 6, 50% glass fiber reinforced, improved flowability, heat and UV stabilized, for injection moulding.

General Information			
Filler / Reinforcement	Glass Fiber,50% Filler by Weight		
Additive	Heat Stabilizer		
	UV Stabilizer		
Features	Good Flow		
	Good UV Resistance		
	Heat Stabilized		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.56	g/cm ³	ISO 1183
Molding Shrinkage ¹			ISO 2577
Across Flow : 23°C, 72 hr	0.40 to 0.60	%	
Flow : 23°C, 72 hr	0.10 to 0.20	%	
Viscosity Number	125	cm ³ /g	ISO 307
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	15500	MPa	ISO 527-2/1
Tensile Stress (Break)	210	MPa	ISO 527-2/5
Tensile Strain (Break)	2.0	%	ISO 527-2/5
Flexural Modulus ²	14000	MPa	ISO 178
Flexural Stress ³	320	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	20	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	95	kJ/m ²	ISO 179/1eU
Notched Izod Impact Strength (23°C)	19	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength (23°C)	90	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	220	°C	ISO 75-2/B
1.8 MPa, Unannealed	210	°C	ISO 75-2/A
Vicat Softening Temperature	215	°C	ISO 306/B50
Melting Temperature	222	°C	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method

Surface Resistivity	1.0E+13	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms·cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Burning Rate	< 100	mm/min	FMVSS 302
Flame Rating (0.800 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	75.0 to 95.0	°C	
Drying Time	2.0 to 4.0	hr	
Processing (Melt) Temp	260 to 280	°C	
Mold Temperature	90.0 to 100	°C	
NOTE			
1.	50% RH		
2.	2.0 mm/min		
3.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

