

# Hostacom HYP 376D 201104

Polypropylene Homopolymer

LyondellBasell Industries

## Message:

Hostacom HYP 376D 201104 is a mineral filled PP homopolymer, with very high melt flow rate. This grade is not intended for medical, pharmaceutical, food and drinking water applications.

| General Information                         |                       |                        |             |
|---|-----------------------|------------------------|-------------|
| Filler / Reinforcement                      | Mineral filler        |                        |             |
| Features                                    | Homopolymer           |                        |             |
|   | High liquidity        |                        |             |
| Uses  | Electrical appliances |                        |             |
| Processing Method                           | Injection molding     |                        |             |
| Physical                                    | Nominal Value         | Unit                   | Test Method |
| Density (23°C)                              | 1.31                  | g/cm <sup>3</sup>      | ISO 1183/A  |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)   | 26                    | g/10 min               | ISO 1133    |
| Melt Volume-Flow Rate (MVR) (230°C/2.16 kg) | 24.0                  | cm <sup>3</sup> /10min | ISO 1133    |
| Mechanical                                  | Nominal Value         | Unit                   | Test Method |
| Tensile Modulus (23°C)                      | 2500                  | MPa                    | ISO 527-2   |
| Tensile Stress (Yield, 23°C)                | 20.0                  | MPa                    | ISO 527-2   |
| Tensile Strain (Yield, 23°C)                | 3.0                   | %                      | ISO 527-2   |
| Impact                                      | Nominal Value         | Unit                   | Test Method |
| Charpy Notched Impact Strength              |                       |                        | ISO 179/1eA |
| 0°C   | 1.5                   | kJ/m <sup>2</sup>      | ISO 179/1eA |
| 23°C  | 2.5                   | kJ/m <sup>2</sup>      | ISO 179/1eA |
| Charpy Unnotched Impact Strength            |                       |                        | ISO 179/1eU |
| 0°C   | 25                    | kJ/m <sup>2</sup>      | ISO 179/1eU |
| 23°C  | 55                    | kJ/m <sup>2</sup>      | ISO 179/1eU |
| Thermal                                     | Nominal Value         | Unit                   | Test Method |
| Heat Deflection Temperature                 |                       |                        |             |
| 0.45 MPa, not annealed                      | 95.0                  | °C                     | ISO 75-2/B  |
| 1.8 MPa, not annealed                       | 55.0                  | °C                     | ISO 75-2/A  |
| Vicat Softening Temperature                 | 92.0                  | °C                     | ISO 306/B   |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

