PETILEN YY F 00556 (HMW)

High Density Polyethylene

PETKIM Petrokimya Holding A.S.

Message:

PETILEN YY F 00556 (HMW) is a High Density Polyethylene product. It can be processed by film extrusion and is available in Asia Pacific, Europe, or North America. Applications of PETILEN YY F 00556 (HMW) include bags/liners and film.

| General Information | | | |
|--|-----------------|----------|-------------|
| Uses | Bags | | |
| | Film | | |
| | Heavy-duty Bags | | |
| | | | |
| Forms | Pellets | | |
| Processing Method | Film Extrusion | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 0.950 to 0.955 | g/cm³ | ASTM D1505 |
| Melt Mass-Flow Rate (MFR) (190°C/2.16 kg) | 0.030 to 0.060 | g/10 min | ASTM D1238 |
| Environmental Stress-Cracking Resistance (F50) | > 600 | hr | ASTM D1693 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength | | | ASTM D638 |
| Yield | 23.0 | MPa | |
| Break | 36.0 | MPa | |
| Tensile Elongation (Break) | 850 | % | ASTM D638 |
| Flexural Modulus | 815 | MPa | ISO 178 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact | 340 | J/m | ASTM D256 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

