

LEXAN™ LAT4000 resin

Polycarbonate

SABIC Innovative Plastics Asia Pacific

Message:

LNP* STAT-LOY* LAT4000 is antistatic compound based on Polycarbonate containing proprietary fillers.

General Information			
UL YellowCard	E45587-236898		
Filler / Reinforcement	Proprietary packing		
Features	Antistatic property		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	0.50 - 0.70	%	Internal method
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	65.7	MPa	Internal method
Tensile Elongation (Break)	220	%	Internal method
Flexural Modulus	2200	MPa	ASTM D790
Flexural Strength	86.3	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	830	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed, 3.20 mm)	130	°C	ASTM D648
CLTE - Flow (-30 to 30°C)	7.0E-5	cm/cm/°C	ASTM E831
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+12	ohms	ASTM D257
Dielectric Constant			ASTM D150
50 Hz	3.20		ASTM D150
60 Hz	3.20		ASTM D150

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT