

Durethan® BKV 40 H2.0 901510

Polyamide 6

LANXESS Asia/Pacific

Message:

PA 6, 40 % glass fibers, injection molding, heat-aging stabilized

General Information				
UL YellowCard		E245249-473597		
Filler / Reinforcement		Glass fiber reinforced material, 40% filler by weight		
Additive		heat stabilizer		
Features		Good heat aging resistance		
Processing Method		Injection molding		
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity				
--	1.46	--	g/cm ³	ASTM D792
23°C	1.46	--	g/cm ³	ISO 1183
Molding Shrinkage				
Vertical flow direction: 280°C, 3.00mm ¹	0.85	--	%	ISO 2577
Vertical flow direction: 120°C, 2 hours, 3.00mm ²	0.070	--	%	ISO 294-4
Flow direction: 280°C, 3.00mm ³	0.16	--	%	ISO 2577
Flow direction: 120°C, 2 hours, 3.00mm ⁴	0.030	--	%	ISO 2577
Water Absorption				ISO 62
Saturated, 23°C	6.0	--	%	ISO 62
Equilibrium, 23°C, 50% RH	1.8	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus				
23°C ⁵	11800	7400	MPa	ASTM D638
23°C	11900	7800	MPa	ISO 527-2/1
Tensile Strength				
Fracture, 23°C	200	120	MPa	ASTM D638
Fracture, 23°C	195	130	MPa	ISO 527-2/5
Tensile Elongation				
Fracture, 23°C	3.0	4.0	%	ASTM D638
Fracture, 23°C	3.0	6.0	%	ISO 527-2/5
Flexural Modulus				
23°C	10800	6800	MPa	ASTM D790
23°C ⁶	11200	7300	MPa	ISO 178/A

Flexural Strength				
23°C	330	200	MPa	ASTM D790
3.5% strain ⁷	305	170	MPa	ISO 178/A
23°C ⁸	310	200	MPa	ISO 178
Flexural Strain at Flexural Strength ⁹ (23°C)	4.0	5.0	%	
ISO Shortname	PA 6, GHR, 14-120, GF40	--		ISO 1874
Residual Moisture Content	0.030 - 0.12		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	15	20	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	70	70	kJ/m ²	ISO 179/1eU
23°C	85	90	kJ/m ²	ISO 179/1eU
Notched Izod Impact				
-40°C, 3.18 mm	130	130	J/m	ASTM D256
23°C, 3.18 mm	160	190	J/m	ASTM D256
-30°C	13	11	kJ/m ²	ISO 180/1A
23°C	18	24	kJ/m ²	ISO 180/1A
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				
0.45 MPa, not annealed, 3.99mm	215	--	°C	ASTM D648
0.45 MPa, not annealed	215	--	°C	ISO 75-2/B
1.8 MPa, not annealed, 3.99mm	200	--	°C	ASTM D648
1.8 MPa, not annealed	200	--	°C	ISO 75-2/A
Vicat Softening Temperature	> 200	--	°C	ISO 306/B120
Melting Temperature ¹⁰	222	--	°C	ISO 11357-3
RTI Elec (1.50 mm)	120	--	°C	UL 746
RTI Imp (1.50 mm)	95.0	--	°C	UL 746
RTI (1.50 mm)	140	--	°C	UL 746
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+14	1.0E+10 - 1.0E+12	ohms	IEC 60093
Volume Resistivity (23°C)	1.0E+15	1.0E+11 - 1.0E+12	ohms·cm	IEC 60093
Dielectric Strength				IEC 60243-1
23°C, 1.00 mm	40	35	kV/mm	IEC 60243-1
23°C, 3.00 mm	40	35	kV/mm	IEC 60243-1
Dielectric Constant				
23°C, 50 Hz ¹¹	4.00	15.0		IEC 60250
23°C, 1 MHz ¹²	4.00	5.00		IEC 60250

23°C, 100 Hz	4.00	10.0		IEC 60250
Dissipation Factor				IEC 60250
23°C, 50 Hz	0.010	--		IEC 60250
23°C, 100 Hz	5.0E-3	0.25		IEC 60250
	0.015	0.12		
23°C, 1 MHz	0.015	0.15		IEC 60250
Comparative Tracking Index				
Solution a	400	--	V	IEC 60112
--	--	375	V	ASTM D3638
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
1.50 mm	HB	--		UL 94
1.60 mm	HB	--		UL 94
3.00 mm	HB	--		UL 94
3.20 mm	HB	--		UL 94
Glow Wire Flammability Index (2.00 mm)	650	--	°C	IEC 60695-2-12
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 - 6.0		hr	
Processing (Melt) Temp	270 - 290		°C	
Mold Temperature	80.0 - 120		°C	
NOTE				
1.	150x150x3; MT 80°C; 400 Bar			
2.	150x150x3			
3.	150x150x3; MT 80°C; 400 Bar			
4.	150x150x3			
5.	1.0 mm/min			
6.	2.0 mm/min			
7.	2.0 mm/min			
8.	2.0 mm/min			
9.	Pull Rate: 2 mm/min; 50% RH			
10.	10°C/min			
11.	Tinfoil Electrodes			
12.	Tinfoil Electrodes			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT