

LEXAN™ 920 resin

Polycarbonate

SABIC Innovative Plastics

Message:

LEXAN 920 is a low viscosity flame retardant grade, especially suitable for electrical applications.

General Information			
UL YellowCard	E45329-236660	E45329-236661	
Additive	Flame retardancy		
Features	Low viscosity		
	Flame retardancy		
Uses	Electrical/Electronic Applications		
RoHS Compliance	RoHS compliance		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	21.0	cm³/10min	ISO 1133
Molding Shrinkage - Flow ¹	0.50 - 0.70	%	Internal method
Water Absorption			ISO 62
Saturated, 23°C	0.35	%	ISO 62
Equilibrium, 23°C, 50% RH	0.15	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	95.0	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2350	MPa	ISO 527-2/1
Tensile Stress			ISO 527-2/50
Yield	63.0	MPa	ISO 527-2/50
Fracture	60.0	MPa	ISO 527-2/50
Tensile Strain			ISO 527-2/50
Yield	6.0	%	ISO 527-2/50
Fracture	85	%	ISO 527-2/50
Flexural Modulus ²	2300	MPa	ISO 178
Flexural Stress	90.0	MPa	ISO 178
Taber Abrasion Resistance (1000 Cycles, 1000 g, CS-17 Wheel)	10.0	mg	Internal method
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			
-30°C ³	11	kJ/m²	ISO 179/1eA
23°C ⁴	60	kJ/m²	ISO 179/1eA

23°C	25	kJ/m ²	ISO 179/2C
Charpy Unnotched Impact Strength ⁵			ISO 179/1eU
-30°C	No Break		ISO 179/1eU
23°C	No Break		ISO 179/1eU
Notched Izod Impact ⁶			ISO 180/1A
-30°C	10	kJ/m ²	ISO 180/1A
23°C	60	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ⁷			ISO 180/1U
-30°C	No Break		ISO 180/1U
23°C	No Break		ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁸			
0.45 MPa, unannealed, 100 mm span	133	°C	ISO 75-2/Be
1.8 MPa, unannealed, 100 mm span	122	°C	ISO 75-2/Ae
Vicat Softening Temperature			
--	140	°C	ISO 306/B50
--	141	°C	ISO 306/B120
Ball Pressure Test (125°C)	Pass		IEC 60695-10-2
CLTE - Flow (23 to 80°C)	7.0E-5	cm/cm/°C	ISO 11359-2
Thermal Conductivity	0.20	W/m/K	ISO 8302
RTI Elec	130	°C	UL 746
RTI Imp	120	°C	UL 746
RTI	125	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms · cm	IEC 60093
Dielectric Strength (3.20 mm, in Oil)	17	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
50 Hz	2.70		IEC 60250
60 Hz	2.70		IEC 60250
1 MHz	2.70		IEC 60250
Dissipation Factor			IEC 60250
50 Hz	1.0E-3		IEC 60250
60 Hz	1.0E-3		IEC 60250
1 MHz	0.010		IEC 60250
Comparative Tracking Index	225	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	V-0		UL 94
Glow Wire Flammability Index			IEC 60695-2-12
1.00 mm	850	°C	IEC 60695-2-12
1.60 mm	960	°C	IEC 60695-2-12
Oxygen Index	35	%	ISO 4589-2

Injection	Nominal Value	Unit
Drying Temperature	120	°C
Drying Time	2.0 - 4.0	hr
Suggested Max Moisture	0.020	%
Hopper Temperature	60.0 - 80.0	°C
Rear Temperature	260 - 280	°C
Middle Temperature	270 - 290	°C
Front Temperature	280 - 300	°C
Nozzle Temperature	270 - 290	°C
Processing (Melt) Temp	280 - 300	°C
Mold Temperature	80.0 - 100	°C

NOTE

- | | |
|----|-----------------|
| 1. | Tensile Bar |
| 2. | 2.0 mm/min |
| 3. | 80*10*3 sp=62mm |
| 4. | 80*10*3 sp=62mm |
| 5. | 80*10*3 sp=62mm |
| 6. | 80*10*3 |
| 7. | 80*10*3 |
| 8. | 120*10*4 mm |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

