

3M™ Dyneon™ Fluoroelastomer FE 5625N

Fluoroelastomer

3M Advanced Materials Division

Message:

3M™ Dyneon™ Fluoroelastomer FE 5625N is a dipolymer made from hexafluoropropylene and vinylidene fluoride. FE 5625N has an incorporated bisphenol cure system.

Special Features

Composition: dipolymer of vinylidene fluoride and hexafluoropropylene

Process targets: injection and transfer moulding, extrusion and calendering

Proprietary incorporated cure technology

Cure profile adjusted for use in automatic multi cavity moulding equipment

Superior flow over regular 3M™ Dyneon™ Fluoroelastomer injection moulding grades

Improved scorch resistance at high moulding temperatures

Excellent mould release - can be used in automated injection moulding equipment

Clean running

Typical Applications

3M™ Dyneon™ Fluoroelastomer FE 5625N is suitable for the production of O-rings in an injection moulding process.

General Information			
Features	Good demoulding performance		
Uses	O-rings		
Appearance	Opacity		
	White-like		
Forms	Thick sheet		
Processing Method	Extrusion		
	Resin transfer molding		
	Calendering		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.80	g/cm ³	Internal method
Mooney Viscosity (ML 1 +10, 121°C)	20	MU	Internal method
Fluorine Content	66	%	Internal method
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	78		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ¹ (100% Strain)	6.80	MPa	ASTM D412A
Tensile Strength ²	13.0	MPa	ASTM D412A
Tensile Elongation ³ (Break)	180	%	ASTM D412A
Compression Set			ASTM D1414
200°C, 70 hr ⁴	16	%	ASTM D1414
200°C, 70 hr ⁵	15	%	ASTM D1414
NOTE			

1.	D mould
2.	Die D
3.	D mould
4.	Post cured 16 hours @ 230°C
5.	Post cured 24 hours @ 260°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

