

RTP 2899 X 106530 B

Polyamide 6

RTP Company

Message:

Nylon 6 Overmolding

General Information			
Uses	overmolding		
RoHS Compliance	Contact manufacturer		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.980	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	1.3 - 2.0	%	ASTM D955
Moisture Content		%	
Peel strength-Nylon 6 ¹	4.4	kN/m	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 10 sec)	55		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
50% strain, 3.18mm ²	1.31	MPa	ASTM D412
100% strain, 3.18mm ³	1.72	MPa	ASTM D412
300% strain, 3.18mm ⁴	3.17	MPa	ASTM D412
Tensile Strength ⁵ (Yield, 3.20 mm)	3.45	MPa	ASTM D412
Tensile Elongation ⁶ (Break)	330	%	ASTM D412
Tear Strength ⁷	16.6	kN/m	ASTM D624
Compression Set ⁸			ASTM D395B
23°C, 22 hr	17	%	ASTM D395B
70°C, 22 hr	38	%	ASTM D395B
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm, ** Values per RTP Company testing.)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	79.4	°C	
Drying Time	2.0 - 4.0	hr	
Dew Point	-17.8	°C	
Processing (Melt) Temp	249 - 282	°C	
Mold Temperature	37.8 - 71.1	°C	
Injection Pressure	34.5 - 103	MPa	
Injection instructions			
Desiccant Type Dryer Required.			

NOTE	
1.	90°, 20 in/min, RTP 55, Interface Failure
2.	C mold, 510mm/min
3.	Mouth die C, 510mm/min
4.	C mold, 510mm/min
5.	C mold, 500 mm/min
6.	Mouth die C, 500 mm/min
7.	C mould
8.	Type 2

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT