

LEXAN™ 105 resin

Polycarbonate

SABIC Innovative Plastics

Message:

Linear, general purpose polycarbonate homopolymer resin. Available only in color 111N, limited package types, and must meet minimum order quantity requirement. External sale requires prior approval of Product Management.

General Information			
Features	General Purpose		
	Homopolymer		
	Linear Polymer Structure		
Uses	General Purpose		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			ASTM D792
--	1.20	g/cm ³	
--	1.19	g/cm ³	
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	7.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.50 to 0.70	%	Internal Method
Water Absorption			ASTM D570
Equilibrium, 23°C	0.35	%	
Equilibrium, 100°C	0.58	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹			ASTM D638
Yield	62.0	MPa	
Break	68.0	MPa	
Tensile Elongation ² (Break)	> 70	%	ASTM D638
Flexural Modulus ³ (50.0 mm Span)	2340	MPa	ASTM D790
Flexural Strength ⁴ (Yield, 50.0 mm Span)	97.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	910	J/m	ASTM D256
Unnotched Izod Impact (23°C)	No Break		ASTM D4812
Instrumented Dart Impact (23°C, Energy at Peak Load)	64.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 6.40 mm	137	°C	
1.8 MPa, Unannealed, 6.40 mm	132	°C	
Vicat Softening Temperature	154	°C	ASTM D1525 ⁵
CLTE - Flow (-40 to 95°C)	6.8E-5	cm/cm/°C	ASTM E831

Optical	Nominal Value	Unit	Test Method
Transmittance (2540 μm)	88.0	%	ASTM D1003
Haze (2540 μm)	1.0	%	ASTM D1003

Injection	Nominal Value	Unit
Drying Temperature	121	°C
Drying Time	3.0 to 4.0	hr
Drying Time, Maximum	48	hr
Suggested Max Moisture	0.020	%
Suggested Shot Size	40 to 60	%
Rear Temperature	288 to 310	°C
Middle Temperature	299 to 321	°C
Front Temperature	310 to 332	°C
Nozzle Temperature	304 to 327	°C
Processing (Melt) Temp	310 to 332	°C
Mold Temperature	82.2 to 116	°C
Back Pressure	0.345 to 0.689	MPa
Screw Speed	40 to 70	rpm
Vent Depth	0.025 to 0.076	mm

NOTE

1. Type I, 50 mm/min
2. Type I, 50 mm/min
3. 1.3 mm/min
4. 1.3 mm/min
5. Rate B (120°C/h), Loading 2 (50 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT