

RTP 205 FR MS

Polyamide 66

RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'
The data for this material has not been recently verified.
Please contact RTP Company for current information prior to specifying this grade.
-Preliminary Product Data per RTP Co.-

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Additive	Molybdenum disulfide lubricant Flame retardancy		
Features	Lubrication Flame retardancy		
RoHS Compliance	Contact manufacturer		
Appearance	Black Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.76	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.20	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.60	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	118		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	13100	MPa	ASTM D638
Tensile Strength	152	MPa	ASTM D638
Tensile Elongation (Break)	2.1	%	ASTM D638
Flexural Modulus	10300	MPa	ASTM D790
Flexural Strength	231	MPa	ASTM D790
Compressive Strength	121	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	80	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	690	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648

0.45 MPa, not annealed	249	°C	ASTM D648
1.8 MPa, not annealed	232	°C	ASTM D648
CLTE - Flow	3.4E-5	cm/cm/°C	ASTM D696
Thermal Conductivity	0.33	W/m/K	ASTM C177
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+14	ohms·cm	ASTM D257
Dielectric Strength	19	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	4.40		ASTM D150
Dissipation Factor (1 MHz)	0.015		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94
Additional Information			
Mold Shrinkage, Linear-Flow, ASTM D-955, 0.25in.: 4mil/in.			
Injection	Nominal Value	Unit	
Drying Temperature	79.4	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.20	%	
Suggested Max Regrind	20	%	
Rear Temperature	246 - 274	°C	
Middle Temperature	246 - 274	°C	
Front Temperature	246 - 274	°C	
Mold Temperature	65.6 - 107	°C	
Injection Pressure	68.9 - 103	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

