

Ravamid® R200 T53

Polyamide 6
Ravago Group

Message:
High impact modified PA6 compound for injection moulding

General Information			
Additive	Impact Modifier		
Features	Impact Modified		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.06	g/cm ³	ISO 2781
Molding Shrinkage			ISO 294-4
Across Flow	1.2	%	
Flow	1.0	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1800	MPa	ISO 527-2
	43.0		
Tensile Stress (Yield)	44.0	MPa	ISO 527-2
Tensile Strain			ISO 527-2
Yield	4.2	%	
Break	60	%	
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	38	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	52.0	°C	ISO 75-2/A
Vicat Softening Temperature	145	°C	ISO 306/B50
Melting Temperature	215 to 220	°C	
Flammability	Nominal Value		Test Method
Flame Rating ¹ (1.60 mm)	HB		Internal Method
NOTE			

1. UL94 internally tested

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

