

Eco Cool Plus SCMP 89

Polybutylene Terephthalate

EcolBiotech Co., Ltd

Message:

Overcomes heat resistance & shrinkage of PLA & PBS
Physical properties applicable to heat resistant,
injection and IT products
Applicable to sheets, air permeable film
blow containers, etc.

General Information			
Features	Biodegradable		
Uses	Blown Containers		
	Film		
	Sheet		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Appearance	Black		
Processing Method	Blow Molding		
	Injection Molding		
	Sheet Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.80	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	55.9	MPa	ASTM D638
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact	23	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	210	°C	
Thermal Conductivity	8.9	W/m/K	Internal Method
Flammability	Nominal Value		Test Method
Flame Rating	V-0		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

