

PRIMATOP HDPE 003955BAS

High Density Polyethylene

Amco Polymers

Message:

Hexene Copolymer

General Information	
Additive	Antistatic
Features	Antistatic
	Copolymer
	Hexene Comonomer
	High ESCR (Stress Crack Resist.)
	High Stiffness
Uses	Blow Molding Applications
	Sheet
Processing Method	Blow Molding
	Sheet Extrusion
	Thermoforming

Physical	Nominal Value	Unit	Test Method
Density	0.955	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.35	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance			
F50	35.0	hr	ASTM D1693B
100% Igepal, F50	45.0	hr	ASTM D1693A

Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	27.6	MPa	ASTM D638
Tensile Elongation ² (Break)	> 600	%	ASTM D638
Flexural Modulus	1380	MPa	ASTM D790

Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -118	°C	ASTM D746

NOTE	
1.	Type IV, 50 mm/min
2.	Type IV, 50 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT