

MAXAMID™ PA66AVL

Polyamide 66
Pier One Polymers, Inc.

Message:

MAXAMID™ PA66AVL is available in natural and black. It contains an internal lubricant for applications requiring low wear and/or coefficient of friction against steel, itself, or other polymers

General Information			
Additive	Lubricant		
Features	Lubrication		
Appearance	Black		
	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.11	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	69.0	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	20	%	ASTM D638
Flexural Modulus (23°C)	2550	MPa	ASTM D790
Flexural Strength (23°C)	96.6	MPa	ASTM D790
Coefficient of Friction			ASTM D1894
Dynamic	0.14		ASTM D1894
Static	0.17		ASTM D1894
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	53	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	74.0	°C	ASTM D648
Peak Melting Temperature	255	°C	ASTM D3418
Injection	Nominal Value	Unit	
Suggested Max Moisture	0.20	%	
Processing (Melt) Temp	290 - 305	°C	
Mold Temperature	38 - 93	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

