

Tenac™-C ZH760

Acetal (POM) Copolymer

Asahi Kasei Chemicals Corporation

Message:

Tenac™-C ZH760 is an Acetal (POM) Copolymer product. It is available in Africa & Middle East, Asia Pacific, Europe, or North America. Applications of Tenac™-C ZH760 include engineering/industrial parts, automotive and housings.

Characteristics include:

- Flame Rated
- Copolymer
- Low Viscosity
- Scratch Resistant
- Wear Resistant

General Information	
UL YellowCard	E48285-476115
Features	Copolymer
	Good Abrasion Resistance
	Low Viscosity
	Low VOC
	Scratch Resistant
Uses	Automotive Applications
	Engineering Parts
	Gears
	Housings

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.41	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	30	g/10 min	ISO 1133
Molding Shrinkage - Flow	1.6 to 2.0	%	Internal Method
Water Absorption (23°C, 24 hr, 50% RH)	0.20	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785
M-Scale	88		
R-Scale	117		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2900	MPa	ISO 527-2
Tensile Stress			
Yield	67.0	MPa	ISO 527-2
--	66.0	MPa	ASTM D638
Tensile Elongation (Break)	30	%	ASTM D638, ISO 527-2
Flexural Modulus			

--	2800	MPa	ASTM D790
--	2750	MPa	ISO 178
Flexural Strength	93.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	6.0	kJ/m ²	ISO 179
Notched Izod Impact	69	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	163	°C	ASTM D648
0.45 MPa, Unannealed	159	°C	ISO 75-2/B
1.8 MPa, Unannealed	124	°C	ASTM D648
1.8 MPa, Unannealed	103	°C	ISO 75-2/A
CLTE - Flow	1.0E-4	cm/cm/°C	ASTM D696, ISO 11359-2
Specific Heat	1470	J/kg/°C	
Thermal Conductivity	0.23	W/m/K	
Flammability	Nominal Value		Test Method
Flame Rating (0.750 mm)	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT