

Retpol® 7250 UV2

Polypropylene Homopolymer

PolyPacific Pty. Ltd.

Message:

Propak 7250 UV2 is a 20% talc filled homopolymer polypropylene compound. It is a low flow injection moulding grade developed for rigid components and is manufactured in accordance with Australian Standard AS 2070, "Plastic Materials for Food Contact Use", and the ingredients used in this formulation are referenced in the US Code of Federal Regulations, Volume 21. It has been stabilized to withstand intermittent exposure to UV radiation.

General Information			
Filler / Reinforcement	Talc,20% Filler by Weight		
Features	Food Contact Acceptable		
	Homopolymer		
	Low Flow		
Uses	Housings		
Agency Ratings	AS 2070-1999		
Forms	Granules		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	3.5	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.00 mm)	1.0 to 1.4	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 3.00 mm)	100		ASTM D785
Durometer Hardness			ASTM D2240
Shore D, 3.00 mm	77		
Shore D, 15 sec, 3.00 mm	72		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (3.00 mm)	31.0	MPa	ASTM D638
Tensile Elongation ² (Break, 3.00 mm)	50	%	ASTM D638
Flexural Modulus (3.00 mm)	2380	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.00 mm)	28	J/m	ASTM D256
Unnotched Izod Impact (3.00 mm)	440	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 3.00 mm	128	°C	
1.8 MPa, Unannealed, 3.00 mm	67.0	°C	
CLTE - Flow (-30 to 30°C, 3.00 mm)	8.0E-5	cm/cm/°C	ASTM D696
Injection	Nominal Value	Unit	

Drying Temperature	100 to 120	°C
Drying Time	2.0 to 4.0	hr
Suggested Max Regrind	10	%
Processing (Melt) Temp	200 to 260	°C
Mold Temperature	20.0 to 60.0	°C
Injection Rate	Moderate-Fast	

NOTE

1. 50 mm/min
2. 50 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT