

Maxxam™ FR PP 307

Polypropylene
PolyOne Corporation

Message:

Maxxam™ FR PP 307 is a Polypropylene product. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.
Characteristics include:
Flame Rated
Flame Retardant
Impact Resistant

General Information			
UL YellowCard	E76261-101455004		
Features	Flame Retardant		
	Medium Impact Resistance		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.02	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) ¹ (230°C/2.16 kg)	2.3	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.0 to 2.0	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ² (Yield)	25.5	MPa	ASTM D638
Tensile Elongation ³ (Break)	100	%	ASTM D638
Flexural Modulus	1000	MPa	ASTM D790
Flexural Strength	33.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm, Injection Molded)	80	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Annealed, 1.57 mm)	85.0	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating	V-0		UL 94
NOTE			
1.	Procedure A		
2.	Type I, 51 mm/min		
3.	Type I, 51 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

