

Tecotek® BC43 UF65 NL CE

Polycarbonate + ABS
Eurotec Engineering Plastics

Message:
PC/ABS, unfilled, heat & UV stabilized, natural, standard grade

General Information			
Additive	Heat Stabilizer		
	UV Stabilizer		
Features	Good UV Resistance		
	Heat Stabilized		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Appearance	Natural Color		
Processing Method	Injection Molding		
Resin ID (ISO 1043)	(PC+ABS)		
Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2250	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	45.0	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	> 50	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ISO 180/1A
-30°C	20	kJ/m ²	
23°C	35	kJ/m ²	
Unnotched Izod Impact Strength			ISO 180/1U
-30°C	No Break		
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	105	°C	ISO 75-2/A
Vicat Softening Temperature	120	°C	ISO 306/B
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	IEC 60093
Volume Resistivity	1.0E+13	ohms · cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94

0.750 mm	HB	
1.60 mm	HB	
Injection	Nominal Value	Unit
Drying Temperature	80.0 to 100	°C
Drying Time	2.0 to 6.0	hr
Hopper Temperature	60.0 to 80.0	°C
Processing (Melt) Temp	240 to 260	°C
Mold Temperature	40.0 to 80.0	°C
Injection Rate	Moderate-Fast	
Holding Pressure	50.0 to 100	MPa
Back Pressure	Low	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

