

ALTECH® NXT PP-B A 2030/451 GF30 CP IM

Polypropylene Copolymer

ALBIS PLASTIC GmbH

Message:

ALTECH® NXT PP-B A 2030/451 GF30 CP IM is a Polypropylene Copolymer (PP Copolymer) product filled with 30% glass fiber. It is available in Asia Pacific, Europe, or North America. Applications of ALTECH® NXT PP-B A 2030/451 GF30 CP IM include automotive and engineering/industrial parts. Characteristics include:

- Flame Rated
- REACH Compliant
- RoHS Compliant
- Chemically Coupled Copolymer

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Heat Stabilizer		
	Impact Modifier		
Features	Chemically Coupled		
	Copolymer		
	Heat Stabilized		
	High Stiffness		
	Impact Modified		
	Ultra High Toughness		
Uses	Automotive Applications		
	Machine/Mechanical Parts		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow : 24 hr	0.40 to 0.60	%	
Flow : 24 hr	0.20 to 0.40	%	
Spiral Flow			
1.00 mm	300	mm	
2.00 mm	700	mm	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	5400	MPa	ISO 527-2
Tensile Stress (Break)	60.0	MPa	ISO 527-2
Tensile Strain (Break)	4.0	%	ISO 527-2

Flexural Modulus	4500	MPa	ISO 178
Flexural Stress	90.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
--	15	kJ/m ²	
-40°C	10	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
--	55	kJ/m ²	
-40°C	50	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	145	°C	ISO 75-2/A
Vicat Softening Temperature	100	°C	ISO 306/B50
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 to 3.0	hr	
Processing (Melt) Temp	200 to 270	°C	
Mold Temperature	20.0 to 90.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT